

# Aufheizvorschrift A 16 / Initial-heating-up instruction A 16 REFRAPATCH®

## Gültig für die Erstaufheizung der genannten Produktgruppen.

Beispiele für die Erstaufheizung von  
verschiedenen Wandstärken auf 800°C  
1. bis 50 mm  
2. bis 100 mm  
Gesamtstärke aller ungetrockneten  
monolithischen Feuerfest-Produkte.

**Beim Aufheizen die maximale Anwen-  
dungstemperatur nicht überschreiten!  
Nach Aufheizen die Betriebstempera-  
tur 12-24 h halten.** Diese Aufheizvor-  
schrift ist eine produktbezogene, allge-  
meine Richtlinie für das Erstaufheizen  
der betreffenden Produkte unter Ideal-  
bedingungen. Eine Anpassung an die  
Gegebenheiten am Ort der Zustellung ist  
daher immer erforderlich. Beachten Sie  
bitte unbedingt unsere „Hinweise zur Auf-  
heizung monolithischer Feuerfestprodukte“.

## Valid for the initial heating-up of the named productgroups.

Examples for the initial heating-up  
of various lining thicknesses to 800°C  
1. up to 50 mm  
2. up to 100 mm  
total thickness of all undried monolithic  
refractory products.

**Do not exceed the maximum service  
temperature when heating-up! After  
heating-up hold the operation tempe-  
rature for 12-24 h.** This initial-heating-  
up instruction is a general guideline for  
the initial heating-up procedure of the res-  
pective products under ideal conditions.  
The actual conditions may vary so that  
the heating up-curve always has to be  
adjusted. Please take notice of our  
“remarks on the heating-up of monolithic  
refractories”.

