

Aufheizvorschrift A 16 / Initial-heating-up instruction A 16 REFRAPATCH®

Gültig für die Erstaufheizung der genannten Produktgruppen.

Beispiele für die Erstaufheizung von
verschiedenen Wandstärken auf 800°C
1. bis 50 mm
2. bis 100 mm
Gesamtstärke aller ungetrockneten
monolithischen Feuerfest-Produkte.

**Beim Aufheizen die maximale Anwen-
dungstemperatur nicht überschreiten!
Nach Aufheizen die Betriebstempera-
tur 12-24 h halten.** Diese Aufheizvor-
schrift ist eine produktbezogene, allge-
meine Richtlinie für das Erstaufheizen
der betreffenden Produkte unter Ideal-
bedingungen. Eine Anpassung an die
Gegebenheiten am Ort der Zustellung ist
daher immer erforderlich. Beachten Sie
bitte unbedingt unsere „Hinweise zur Auf-
heizung monolithischer Feuerfestprodukte“.

Valid for the initial heating-up of the named productgroups.

Examples for the initial heating-up
of various lining thicknesses to 800°C
1. up to 50 mm
2. up to 100 mm
total thickness of all undried monolithic
refractory products.

**Do not exceed the maximum service
temperature when heating-up! After
heating-up hold the operation tempe-
rature for 12-24 h.** This initial-heating-
up instruction is a general guideline for
the initial heating-up procedure of the res-
pective products under ideal conditions.
The actual conditions may vary so that
the heating up-curve always has to be
adjusted. Please take notice of our
“remarks on the heating-up of monolithic
refractories”.

